

Phase Transformations and Structural Relaxation Processes in Supercooled Mesogenic /-p-Aminoxybenzylidene/p-Toluidine/

V.P. Bukalo, V.Ye. Pogorelov, and Yu.A. Astashkin

Physics Department

Kyiv National Taras Shevchenko University

Prospect Glushkova 6, 03022 Kyiv, Ukraine

The developments of phase transitions and structural relaxation processes were investigated in vibration Raman spectra under slow heating of supercooled /-p-aminoxybenzylidene/p-toluidine/ (ABT).

A sample of ABT heated to the isotropic liquid state ($T=343$ K) was cooled in liquid nitrogen ($T=78$ K). Then it was heated at a rate of 2 K/min, and Raman spectra in regions $1150\text{--}1210\text{ cm}^{-1}$ and $1550\text{--}1650\text{ cm}^{-1}$ were measured. It was found that Raman bandwidths of supercooled liquid crystals coincide with same parameters of nematic and isotropic liquid. Then at $T\sim 220$ K amorphous object is transformed into crystal. It is developed in narrowing of bands.

For study of the dependence of crystallization temperature with thermal pre-history, the annealing of supercooled sample at two temperature points ($T=198, 210$ K) with simultaneous registration of Raman spectra. was made. The exponential time dependence of bandwidths with characteristic times (τ) $\sim 7.2 \times 10^3$ c ($T=198$ K) and $\sim 1.5 \times 10^4$ c ($T=210$ K). was obtained. Using these values and taking into account the Boltzmann-Arrhenius equation: $\tau = B \cdot \exp(U/kT)$, the activation energy ($u = UN_A = 21$ kJ/mol) of amorphous state-crystal relaxation process and time ($B = 4.0 \times 10^{-2}$ c) of attempt of structural elements for potential barrier overcoming was estimated. It allowed the curve of structural relaxation time temperature dependence around region of amorphous state crystallization to be obtained